

KYNAR FLEX®

TECHNICAL DATA SHEET

KYNAR FLEX® 2801-00 POWDER

FLUORINATED COPOLYMER POWDER

KYNAR FLEX® resins are fluorinated thermoplastic copolymers. Outstanding characteristics: chemical resistance, imperviousness to UV, high barrier properties, high purity, good mechanical and thermo-mechanical properties. This product is NSF/ANSI/CAN 61 certified. KYNAR FLEX® 2801 resin is the powder form of the KYNAR FLEX® 2800-00 resin. To be used an additive in LLDPE to improve the extrusion rate.

TYPE

PVDF

MAIN APPLICATIONS

- Polymer Processing Aid

DELIVERY FORM

- Powder

RHEOLOGICAL PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Melt viscosity, 230°C (445°F) at 100 s-1	23 - 27	kPo	ASTM D3835
Melt flow index (MFR), 235°C / 5 kg (455°F / 11 lb)	3 - 8	g/10min	ASTM D1238
Melt volume flow rate (MVR), 230°C / 5 kg (446°F / 11 lb)	0.5	cm³/10min	ISO 1133

MECHANICAL PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Yield stress, 23°C (73°F)	20 - 34.5	MPa	ASTM D638
Yield strain, 23°C (73°F), 50 mm/min	15	%	ISO 527-1/-2
Stress at break, 23°C (73°F)	17.2 - 34.5	MPa	ASTM D638
Nominal strain at break, 23°C (73°F), 50 mm/min	>50	%	ISO 527-1/-2
Flexural modulus, 23°C (73°F)	483 - 758	MPa	ASTM D790
Compression strength, 23°C (73°F)	31 - 41.4	MPa	ASTM D695
Izod impact unnotched strength, 23°C (73°F)	No Break		ASTM D256
Izod impact notched strength, 23°C (73°F)	0.534 - 1.07	J/m	ASTM D256
Hardness, Shore D	60 - 70		ASTM D2240
Tensile modulus, 23°C (73°F)	700	MPa	ASTM D638
Coefficient of friction dynamic vs steel, 23°C (73°F)	0.33		ASTM D1895
Coefficient of friction static vs steel, 23°C (73°F)	0.33		ASTM D1894
Abrasion resistance, Wheel CS 17, load 1 kg, 1000 cycles	16 - 19	mg	ASTM G195-13A

KYNAR FLEX® 2801-00 POWDER

THERMAL PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Glass transition temperature, 10°C/min	-40	°C	ISO 11357-1/-2
Vicat softening temperature, 50N at 50°C/h	79	°C	ISO 306
Limiting oxygen index (LOI)	42	%	ASTM D2863
Yellow card available	yes		
Coefficient of linear thermal expansion, 23°C (73°F)	126 - 185	10E-6 / °K	ASTM D696
Specific heat temperature, 23°C (73°F)	745 - 958		ISO 11357-1/-2
Heat deflection temperature, 1.8 MPa	48	°C	ISO 75-1/-2
Heat deflection temperature, 1.8 MPa, 138°C/h	40 - 55	°C	ASTM D648
Heat deflection temperature, 0.45 MPa, 138°C/h	60-75	°C	ASTM D648
Thermal conductivity	0.144 - 0.18	W/m-K	ASTM D433
Melting temperature, 10°C/min	143	°C	ISO 11357-1/-3

ELECTRICAL PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Dielectric constant, 1kHz	3.5 - 10.6		ASTM D150
Dielectric strength, 23°C (73,4°F)	1.3 - 1.5	kV/mm	ASTM D149
Relative permittivity, 1MHz	7		IEC 62631-2-1
Relative thermal index	130		
Dissipation factor, 1MHz	2330	E-4	IEC 62631-2-1
Dissipation factor	0.02 - 0.21		ASTM D150

OTHER PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Specific gravity, 23°C (73°F)	1.77 - 1.8	g/cm³	
Water absorption, Saturated in water at 23°C (73°F)	0.03	%	ISO 62

PACKAGING

Available packaging:

- 20 kg / 45 lb metal drum
- 20 kg / 45 lb plastic drum
- 320 kg / 700 lb big bag
- 45 kg / 100 lb drums
- 45 kg / 100 lb plastic drum

SPECIAL CHARACTERISTICS

- Flame & smoke