

PEBAX®

3533 SA 01 MED

Polyether block amide **Pebax® 3533 SA 01 MED resin** is a thermoplastic elastomer made of flexible polyether and rigid polyamide.

This grade offers the highest quality and it is specially designed to meet the stringent requirements of the medical applications such as minimally invasive devices.

Upon request, letters regarding USP Class VI compliance can be provided.

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Molding Shrinkage, parallel	0.5 / *	%	ISO 294-4, 2577
Molding Shrinkage, normal	0.8 / *	%	ISO 294-4, 2577
MECHANICAL PROPERTIES			
Tensile Modulus	19 / 18	MPa	ISO 527-1/-2
	2760 / 2610	psi	
Stress at 50% Strain	4 / 4	MPa	ISO 527-1/-2
	580 / 580	psi	
Strain at Break	>50 / >50	%	ISO 527-1/-2
Strain at Break TPE	>300 / *	%	ISO 527-1/-2
Stress at Break TPE	39 / *	MPa	ISO 527-1/-2
	5660 / *	psi	
Shore A Hardness	82 / *	-	ISO 868
Shore D Hardness	25 / *	-	ISO 868
Charpy Impact Strength, +23°C	- / No Break	kJ/m²	ISO 179/1eU
Charpy Impact Strength, -30°C	- / No Break	kJ/m²	ISO 179/1eU
Charpy Notched Impact Strength, +23°C	- / No Break	kJ/m²	ISO 179/1eA
Charpy Notched Impact Strength, -30°C	- / No Break	kJ/m²	ISO 179/1eA
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	144 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES			
Water Absorption	1.2 / *	%	Sim. to ISO 62
Humidity Absorption	0.4 / *	%	Sim. to ISO 62
Density	1000 / 1000	kg/m³	ISO 1183
	1 / 1	g/cm³	

PEBAX[®]

3533 SA 01 MED

MAIN APPLICATIONS: • Catheters

• Flexible injected parts

PACKAGING:

This grade is delivered dried in sealed packaging (25 kg bags) ready to be processed.

SHELF LIFE:

Two years from the delivery. For any use above this limit, please refer to our technical services.

Processing conditions:

- Typical melt temperature (Min / Recommended / Max) : 180°C / 210°C / 240°C.
- Typical mold temperature : 10 – 30°C.
- Drying time and temperature (only necessary for bags opened for more than two hours) : 4-8 hours at 55-65°C.

Processing conditions:

- Typical melt temperature (Min / Recommended / Max) : 190°C / 205°C / 220°C.
- Drying time and temperature (only necessary for bags opened for more than two hours) : 4-8 hours at 55-65°C.

PROCESSING	
Injection Molding, Film Extrusion, Other Extrusion	
DELIVERY FORM	
Pellets	
ADDITIVES	
Lubricants	
SPECIAL CHARACTERISTICS	
Heat Stabilized	
REGIONAL AVAILABILITY	
North America, Europe, Asia Pacific, South and Central America, Near East/Africa	