

PEBAX®

7033 SA 01 MED

Polyether block amide **Pebax® 7033 SA 01 MED resin** is a thermoplastic elastomer made of flexible polyether and rigid polyamide.

This grade offers the highest quality and it is specially designed to meet the stringent requirements of the medical applications such as minimally invasive devices.

Pebax® 7033 SA 01 MED resin also offers an excellent combination of properties such as: kink resistance, low friction coefficient and superior dynamic response.

Upon request, letters regarding USP Class VI compliance can be provided.

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Molding Shrinkage, parallel	1.2 / *	%	ISO 294-4, 2577
Molding Shrinkage, normal	1.5 / *	%	ISO 294-4, 2577
MECHANICAL PROPERTIES			
Tensile Modulus	414 / 390	MPa	ISO 527-1/-2
	60000 / 56600	psi	
Yield stress	23 / 22	MPa	ISO 527-1/-2
	3340 / 3190	psi	
Yield strain	22 / 20	%	ISO 527-1/-2
Nominal Strain at Break	>50 / >50	%	ISO 527-1/-2
Abrasion Resistance	41 / *	mm ³	ISO 4649
Shore D Hardness	61 / *	-	ISO 868
Charpy Impact Strength, +23°C	- / No Break	kJ/m ²	ISO 179/1eU
Charpy Impact Strength, -30°C	- / No Break	kJ/m ²	ISO 179/1eU
Charpy Notched Impact Strength, +23°C	- / 120	kJ/m ²	ISO 179/1eA
	- / 57.1	ftlb/in ²	
Charpy Notched Impact Strength, -30°C	- / 20	kJ/m ²	ISO 179/1eA
	- / 9.51	ftlb/in ²	
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	172 / *	°C	ISO 11357-1/-3
Vicat Softening Temperature, 50°C/h 50N	106 / *	°C	ISO 306
	223 / *	°F	
OTHER PROPERTIES			
Water Absorption	1.43 / *	%	Sim. to ISO 62
Humidity Absorption	0.76 / *	%	Sim. to ISO 62
Density	1010 / -	kg/m ³	ISO 1183
	1.01 / -	g/cm ³	

PEBAX®

7033 SA 01 MED

MAIN APPLICATIONS: • Tubings like angiography and angioplasty catheters • Flexible injected parts

PACKAGING:

This grade is delivered dried in sealed packaging (20 kg bags) ready to be processed.

SHELF LIFE:

Two years from the delivery. For any use above this limit, please refer to our technical services.

Processing conditions:

- Typical melt temperature (Min / Recommended / Max) : 230°C / 260°C / 290°C
- Typical mold temperature : 25 – 60°C
- Drying time and temperature (only necessary for bags opened for more than two hours) : 5-7 hours at 70-80°C

Processing conditions:

- Typical melt temperature (Min / Recommended / Max) : 220°C / 235°C / 250°C.
- Drying time and temperature (only necessary for bags opened for more than two hours) : 5-7 hours at 70-80°C.

PROCESSING	
Injection Molding, Other Extrusion	
DELIVERY FORM	
Pellets	
SPECIAL CHARACTERISTICS	
Heat Stabilized	
REGIONAL AVAILABILITY	
North America, Europe, Asia Pacific, South and Central America, Near East/Africa	