



**TotalEnergies**

Refining & Chemicals  
Polymers

+135-3858-6433 (GuangDong)  
+188-1699-6168 (ShangHai)  
+852-6957-5415 (HongKong)

**EPS XLR 5550**

Technical data sheet  
Expandable Polystyrene beads – Excell-R®  
Produced in Europe

## Description

EPS XLR 5550 Excell-R® is a grey colour expandable polystyrene (EPS) product intended for the production of foams with improved thermal insulation properties compared to conventional EPS.

EPS XLR 5550 Excell-R® can be processed into foamed insulation boards & shaped articles, with improved thermal insulation properties. Typical applications are foamed insulation boards; plaster covered insulation boards, sandwich panels & cavity wall filling. EPS XLR 5550 does not contain a flame retardant. Product intended for normal use in accordance with the applicable legislation with regard to the reaction to fire.

## Characteristics

Beads	Standard	Unit	Typical Value
Typical bead diameter		mm	1.25
Bead size diameter distribution (0.9 – 1.6 mm)		%	> 90
Typical bulk density		g/l	625
<b>Blowing agent</b>			
Type			Pentane
Approximate quantity at time of packaging		%	< 5.6
<b>Typical</b>			
Moisture content		%	< 0.3
Typical beads apparent density obtainable in single pre-foaming		g/l	16-18
Typical beads apparent density obtainable in two step pre-foaming		g/l	10-12

Expandable Polystyrene