



TotalEnergies

Refining & Chemicals
Polymers

+135-3858-6433 (GuangDong)
+188-1699-6168 (ShangHai)
+852-6957-5415 (HongKong)

Polypropylene PPC 10810

Technical data sheet
Polypropylene – Heterophasic Copolymer
Produced in Europe

Description

Polypropylene PPC 10810 is a high flow, very high impact heterophasic copolymer with a Melt Flow Index of 18 g/10min.

Polypropylene PPC 10810 is easy to process and has been developed for the injection moulding of automotive parts that require a very high impact resistance even at low temperature.

Characteristics

	Method	Unit	Typical Value
Rheological properties			
Melt Flow Index 230°C/2.16 kg	ISO 1133	g/10 min	18
Mechanical properties			
Tensile Strength at Yield	ISO 527-2	MPa	19
Elongation at Yield	ISO 527-2	%	6
Tensile modulus	ISO 527-2	MPa	900
Flexural modulus	ISO 178	MPa	950
Izod Impact Strength (notched)	ISO 180	kJ/m ²	
at 23°C			>50
at -20°C			8
Charpy Impact Strength (notched)	ISO 179	kJ/m ²	
at 23°C			>50
at -20°C			7.5
at -30°C			6.5
Falling Weight at -30°C	ISO-6603-2	---	Ductile
Thermal properties			
Melting Point	ISO 3146	°C	165
Vicat Softening Point	ISO 306	°C	
50N-50°C per hour			65
10N-50°C per hour			135
Heat Deflection Temperature	ISO 752	°C	
1.80 MPa - 120°C per hour			50
0.45 MPa - 120°C per hour			85
Other physical properties			
Density	ISO 1183	g/cm ³	0.905
Bulk Density	ISO 1183	g/cm ³	0.525

Polypropylene