



TotalEnergies

Refining & Chemicals
Polymers

+135-3858-6433 (GuangDong)
+188-1699-6168 (ShangHai)
+852-6957-5415 (HongKong)

Polyethylene Lumicene® mPE M 2710 AP

Technical data sheet
Metallocene Polyethylene BLOWN FILM
Produced in Europe

Description

Lumicene® mPE M 2710 AP is a second generation metallocene based Low Density Polyethylene with hexene as comonomer.

Lumicene® mPE M 2710 AP can be processed at high output rates with low extrusion pressure, excellent bubble stability and gauge control in comparison with conventional LLDPE and first generation metallocene based polyethylene. The combination of these features brings a significant downgauging potential.

Lumicene® mPE M 2710 AP is especially dedicated to film applications where high gloss and high transparency are required, particularly in blend and in coextrusion with LLDPE or LDPE.

Lumicene® mPE M 2710 AP is suited for many applications in the field of consumer, industrial, food or hygiene packaging such as bags, deep freeze, collation shrink and lamination.

Lumicene® mPE M 2710 AP does not contain any Polymer Processing Aid based on Perfluoroalkyl Substance (PFAS)

Characteristics

Property	Method	Unit	Typical value
Density	ISO 1183	g/cm ³	0.927
Melt Flow Rate (190°C/2.16 kg)	ISO 1133	g/10 min	0.9
Melting temperature	ISO 11357	°C	119
Vicat temperature	ISO 306	°C	118

Values indicated are typical for this product. Density and MFR are properties routinely measured during "the standard quality control procedure". The other figures are generated by tests not included in the "standard quality control procedure", and are given for information only.
Data are not intended for specification purposes.

Polyethylene



TotalEnergies

Refining & Chemicals
Polymers

+135-3858-6433 (GuangDong)
+188-1699-6168 (ShangHai)
+852-6957-5415 (HongKong)

Polyethylene Lumicene® mPE M 2710 AP

Blown film properties

These values have been measured on a 40 µm blown film.

Property	Method	Unit	Typical value
Tensile Strength at Yield MD/TD (**)	ISO 527-3	MPa	13.5/14
Tensile Strength at Break MD/TD (**)	ISO 527-3	MPa	51/48
Elongation at Break MD/TD (**)	ISO 527-3	%	650/720
Elmendorf MD/TD (**)	ISO 6383-2	N/mm	60/160
Dart test	ISO 7765-1	g	200
Haze	ISO 14782	%	6.5
Gloss 45°	ASTM D2457		70

(*) Figures stated hereabove are obtained using laboratory test specimens produced with the following extrusion conditions: 45 mm screw diameter, L/D = 30, die diameter = 120 mm, die gap = 1.4 mm, BUR = 2.5:1, temperature = 210°C.

(**) MD : Machine Direction, TD : Transverse Direction