



**TotalEnergies**

Refining & Chemicals  
Polymers

+135-3858-6433 (GuangDong)  
+188-1699-6168 (ShangHai)  
+852-6957-5415 (HongKong)

## Polyethylene Lumicene® mPE M 5510 AP

Technical data sheet  
Metallocene Polyethylene BLOWN FILM  
Produced in Europe

### Description

Lumicene® mPE M 5510 AP is a second generation metallocene high density homopolymer Polyethylene.

Lumicene® mPE M 5510 AP can be processed at high output rates with low extrusion pressure, excellent bubble stability and gauge control in comparison with conventional LLDPE and first generation metallocene based polyethylene. The outstanding stiffness combined with good optical properties brings a significant down-gauging potential.

The high density of Lumicene® mPE M 5510 AP enables its use in applications with moisture barrier requirements, such as dry food packaging, and brings improved heat resistance, compared to commonly used HDPE.

Lumicene® mPE M 5510 AP is suited for many applications in the field of consumer, industrial, food or hygiene packaging such as bags, heavy-duty sacks, automatic packaging specialty film, mailing film and lamination.

Lumicene® mPE M 5510 AP does not contain any Polymer Processing Aid based on Perfluoroalkyl Substance (PFAS)

### Characteristics

Property	Method	Unit	Typical value (*)
Density	ISO 1183	g/cm <sup>3</sup>	0.955
Melt Flow Rate (190°C/2.16 kg)	ISO 1133	g/10 min	1.2
Melting temperature	ISO 11357	°C	134
Vicat temperature	ISO 306	°C	133

(\*) Values indicated are typical for this product. Density and MFR are routinely measured during the standard quality control procedure. The other figures are generated by tests not included in the standard quality control procedure, and are given for information only. Data are not intended for specification purposes.

Polyethylene



**TotalEnergies**

Refining & Chemicals  
Polymers

+135-3858-6433 (GuangDong)  
+188-1699-6168 (ShangHai)  
+852-6957-5415 (HongKong)

## Polyethylene Lumicene® mPE M 5510 AP

### Blown film properties

These values have been measured on a 40 µm blown film.

Property	Method	Unit	Typical value (*)
Tensile Strength at Yield MD/TD**	ISO 527-3	MPa	27.5/28
Tensile Strength at Break MD/TD**	ISO 527-3	MPa	57/45
Elongation at Break MD/TD**	ISO 527-3	%	870/910
Elmendorf MD/TD**	ISO 6383-2	N/mm	11/90
Dart test	ISO 7765-1	g	100
Haze	ISO 14782	%	24
Gloss 45°	ASTM D2457		40

(\*) Figures stated hereabove are obtained using laboratory test specimens produced with the following extrusion conditions: 45 mm screw diameter, L/D = 30, die diameter = 120 mm, die gap = 1.4 mm, BUR = 2.5:1, temperature = 210°C.

(\*\*) MD : Machine Direction, TD : Transverse Direction