



TotalEnergies

Refining & Chemicals
Polymers

+135-3858-6433 (GuangDong)
+188-1699-6168 (ShangHai)
+852-6957-5415 (HongKong)

Polyethylene Aceso® PEM 2408

Technical data sheet
Low Density Polyethylene Medical
Produced in Europe

Description

Aceso® PEM 2408 is a low density polyethylene made by a high pressure autoclave process without antioxidant. This grade is particularly suitable for the blown film, injection blow molding and extrusion blow molding processes.

Aceso® PEM 2408 has been specifically designed for the manufacture of healthcare products and pharmaceutical packaging like bags, pouches, medical films, tubes, etc... However it is recommended to contact your local sales representative to obtain specific information and individual certificates regarding compliance to regulations.

Characteristics

Property	Method	Unit	Typical value
Density	ISO 1183	g/cm ³	0.924
Melt Flow Rate (190°C/2.16 kg)	ISO 1133	g/10 min	0.8
Melting temperature	ISO 11357	°C	111
Vicat temperature	ISO 306	°C	99

Values indicated are typical for this product. Density and MFR are properties routinely measured during "the standard quality control procedure". The other figures are generated by tests not included in the "standard quality control procedure" and are given for information only. Data are not intended for specification purposes.

Polyethylene