

## Description

EVA 1005 VN 35 is made by a high pressure tubular process.  
Grade for flexible films, with high transparency and outstanding mechanical properties.

## Characteristics

Property	Method	Unit	Typical value
Melt Flow Rate (190°C/2.16 kg)	ISO 1133	g/10 min	0.5
VA Content	Total Petrochemicals	%	12
Melting temperature	ISO 11357	°C	91
Vicat temperature	ISO 306	°C	72
Elasticity Modulus	ISO 527-2	MPa	70
Density	ISO 1183	g/cm <sup>3</sup>	0.935

Values indicated are typical for this product. VA Content and MFR are properties routinely measured during "the standard quality control procedure". The other figures are generated by tests not included in the "standard quality control procedure", and are given for information only. Data are not intended for specification purposes.

## Additives

EVA 1005 VN 35 doesn't contain antioxidant.

## Processing

Advised temperature profile: 150 to 180°C.  
The possible range of film thickness is 30 to 200 µm, depending on extrusion conditions.

## Blown film properties

These values have been measured on a 40 µm blown film.

Property	Method	Unit	Typical value (*)
Tensile Strength at Yield MD/TD	ISO 527-3	MPa	6.4/5.6
Tensile Strength at Break MD/TD	ISO 527-3	MPa	39/37
Elongation at Break MD/TD	ISO 527-3	%	380/650
Elmendorf MD/TD	ISO 6383-2	N/mm	15/20
Dart test	ISO 7765-1	g	630
Haze	ISO 14782	%	4.4

(\*) Figures stated hereabove are obtained using laboratory test specimens produced with the following extrusion conditions: 45 mm screw diameter, L/D = 30, die diameter = 120 mm, die gap = 1.4 mm, BUR = 2.5:1, temperature = 170°C.