

Refining & Chemicals Polymers

Technical data sheet
Ethylene Vinyl Acetate Copolymer BLOWN FILM
Produced in Europe

## **Description**

EVA 1005 VN 2 is made by a high pressure tubular process.

Grade for transparent and resistant films.

Application examples: Stretch, coextrusion, frozen food, agricultural film.

#### **Characteristics**

| Property                       | Method               | Unit     | Typical<br>value |
|--------------------------------|----------------------|----------|------------------|
| Melt Flow Rate (190°C/2.16 kg) | ISO 1133             | g/10 min | 0.5              |
| VA Content                     | Total Petrochemicals | %        | 5.5              |
| Melting temperature            | ISO 11357            | °C       | 104              |
| Vicat temperature              | ISO 306              | °C       | 90               |
| Elasticity Modulus             | ISO 527-2            | MPa      | 160              |
| Density                        | ISO 1183             | g/cm³    | 0.925            |

Values indicated are typical for this product. VA Content and MFR are properties routinely measured during "the standard quality control procedure". The other figures are generated by tests not included in the "standard quality control procedure", and are given for information only. Data are not intended for specification purposes.

### **Additives**

Antioxidant: Yes

### **Processing**

Advised temperature profile: 160 to 190°C.

The possible range of film thickness is 45 to 300 µm, depending on extrusion conditions.

**Refining & Chemicals** Polymers

# **Blown film properties**

These values have been measured on a 40 µm blown film.

| Property                        | Method     | Unit | Typical value (*) |
|---------------------------------|------------|------|-------------------|
| Tensile Strength at Yield MD/TD | ISO 527-3  | MPa  | 9.5/8.5           |
| Tensile Strength at Break MD/TD | ISO 527-3  | MPa  | 32/27             |
| Elongation at Break MD/TD       | ISO 527-3  | %    | 300/570           |
| Elmendorf MD/TD                 | ISO 6383-2 | N/mm | 34/33             |
| Dart test                       | ISO 7765-1 | g    | 340               |
| Haze                            | ISO 14782  | %    | 8.8               |

+135-3858-6433 (GuangDong) +188-1699-6168 (ShangHai) +852-6957-5415 (HongKong)

<sup>(\*)</sup> Figures stated hereabove are obtained using laboratory test specimens produced with the following extrusion conditions: 45 mm screw diameter, L/D = 30, die diameter = 120 mm, die gap = 1.4 mm, BUR = 2.5:1, temperature = 180°C.