

+135-3858-6433 (GuangDong) +188-1699-6168 (ShangHai) +852-6957-5415 (HongKong)

Refining & Chemicals Polymers Technical data sheet Ethylene Vinyl Acetate Copolymer BLOWN FILM Produced in Europe

Description

EVA 1003 VN 4 is made by a high pressure tubular process.

Grade for flexible films, with very high transparency and outstanding mechanical properties. Application examples: High strength stretch film, green house film, film for food packaging (coextrusion), stretch hood.

Characteristics

| Property | Method | Unit | Typical value |
|--------------------------------|----------------------|----------|---------------|
| Melt Flow Rate (190°C/2.16 kg) | ISO 1133 | g/10 min | 0.4 |
| VA Content | Total Petrochemicals | % | 13.5 |
| Melting temperature | ISO 11357 | °C | 92 |
| Vicat temperature | ISO 306 | °C | 74 |
| Elasticity Modulus | ISO 527-2 | MPa | 70 |
| Density | ISO 1183 | g/cm³ | 0.935 |

Values indicated are typical for this product. VA Content and MFR are properties routinely measured during "the standard quality control procedure". The other figures are generated by tests not included in the "standard quality control procedure", and are given for information only. Data are not intended for specification purposes.

Additives

Antioxidant: Yes

Processing

Advised temperature profile: 150 to 180°C. The possible range of film thickness is 30 to 300 μ m, depending on extrusion conditions.



Polymers

Blown film properties

These values have been measured on a 40 μm blown film.

| Property | Method | Unit | Typical value (*) |
|---------------------------------|------------|------|-------------------|
| Tensile Strength at Yield MD/TD | ISO 527-3 | MPa | 6.5/5 |
| Tensile Strength at Break MD/TD | ISO 527-3 | MPa | 38/38 |
| Elongation at Break MD/TD | ISO 527-3 | % | 310/590 |
| Elmendorf MD/TD | ISO 6383-2 | N/mm | 13/28 |
| Dart test | ISO 7765-1 | g | 650 |
| Haze | ISO 14782 | % | 2.5 |

(*) Figures stated hereabove are obtained using laboratory test specimens produced with the following extrusion conditions: 45 mm screw diameter, L/D = 30, die diameter = 120 mm, die gap = 1.4 mm, BUR = 2.5:1, temperature = $180^{\circ}C$.