

Description

HDPE 2004 TN52 is a high density polyethylene (HDPE) intended for the extrusion of corrugated pipes.

HDPE 2004 TN52 is best processed between 190 and 230°C

Characteristics

Property	Method	Unit	Typical value (*)
Density	ISO 1183	g/cm ³	0.954
Melt Flow Rate (190°C/21.6 kg)	ISO 1133	g/10 min	22

(*) Data not intended for specification purposes