+135-3858-6433 (GuangDong) +188-1699-6168 (ShangHai) +852-6957-5415 (HongKong)

Technical Data Sheet
Easy flow impact Polystyrene
Manufactured in Europe

Description

POLYSTYRENE IMPACT 6540 is an easy flowing, high impact polystyrene with a good balance of mechanical and thermal properties. This resin combines physical properties such as the flow necessary for large or complex mouldings, the impact resistance for good mechanical properties in thin wall sections and good thermal properties for articles subjected to elevated temperatures in use. The combination of properties also offers high productivity.

Applications

POLYSTYRENE IMPACT 6540 satisfies the requirements of a wide range of moulding applications. Toys, television housing, food packaging, refrigerator, computer keyboards, office equipment, household items...

Properties

| Rheological | Method | Unit | Value |
|--|------------|--------|----------|
| Melt flow index (200°C-5kg) | ISO 1133 H | g/10mn | 11.5 |
| Thermal | | | |
| Vicat softening point 10N (T° increase = 50°C/h) | ISO 306A50 | °C | 92 |
| Vicat softening point 50N (T° increase = 50°C/h) | ISO 306B50 | °C | 83 |
| HDT unannealed under 1.8 MPa | ISO 75-2A | °C | 68 |
| HDT annealed under 1.8 MPa | ISO 75-2A | °C | 80 |
| Coefficient of linear thermal expansion | | mm/°C | 9.10 E-5 |
| Mechanical | | | |
| Notched Izod impact strength | ISO 180/1A | kJ/m² | 9.5 |
| Tensile strength at yield | ISO 527-2 | MPa | 25 |
| Tensile strength at break | ISO 527-2 | MPa | 20 |
| Elongation at break | ISO 527-2 | % | 45 |
| Flexural modulus | ISO 178 | MPa | 2100 |
| Rockwell hardness | ISO 2039-2 | | R 78 |
| Electrical | | | |
| Dielectric strength | | kV/mm | 150 |
| Surface resistivity | ISO IEC 93 | Ohms | >10 E+13 |
| Miscellaneous | | | |
| Density | ISO 1183 | g/cm³ | 1.04 |
| Moulding shrinkage | | % | 0.4-0.7 |
| Water absorption | ISO 62 | % | <0.1 |

General Information

- > Standard properties: All tests carried out at 23°C unless otherwise stated. Mechanical properties are measured on injection moulded tests specimens.
- ➤ Bulk density: bulk density is approximately 0.6 g/cm3.

