

Technical Data Sheet Compound Polystyrene Manufactured in China

## Description

TOTAL POLYSTYRENE 260-25 is an easy flow, high impact polystyrene for injection molding application.

+135-3858-6433 (GuangDong)

- > 260-25 contains a significant level of recycled polystyrene.
- > This grade is recommended for manufacturing of articles which require good dimensional stability.

## Applications

- TV Cover
- Office Automation
- Electric and Electronic

Properties	Method	Unit	Value (*)
Rheological			
Melt Flow Index (200°C/5kg)	ISO 1133	g/10min	8.00
Thermal			
Vicat Softening Point 10N (T° increase = 50°C/h)	ISO 306	°C	90
Coefficient of Linear Thermal Expansion	-	mm/°C	8.90
Mechanical			
Notched Izod Impact Strength	ISO 180	kJ/m²	7.5
Tensile Strength at Yield	ISO 527	MPa	20
Elongation at Break	ISO 527	%	30
Flexural Modulus	ISO 178	MPa	1800
Electrical			
Dielectric Strength	-	kV/mm	160
Surface Resistivity	ISO IEC 93	Ohms	>10 <sup>13</sup>
Others			
Density	ISO 1183	g/cm <sup>3</sup>	1.04
Moulding Shrinkage	-	%	0.4-0.7
Water Absorption	ISO 62	%	<0.1
UL 94 Class	UL 94	-	HB

(\*) Data not intended for specification purposes.

\*All tests have been carried out at 23°C unless otherwise stated.

\*Mechanical properties have been measured on injection molded test specimens.

\*Bulk density is approximately  $0.6 \text{ g/cm}^3$ .

## **General Information**

- > Processing condition: Temperatures during extrusion/injection should be below 240°C.
- Recommended Pre-dry condition: 70°C for 2 hours.