

Refining & Chemicals Polymers

Technical Data Sheet Specialty Compounds Polyethylene Rotational Moulding Produced in Europe

Description

TPSeal® M3671 is a new generation metallocene Medium Density Polyethylene (mMDPE) with hexene as comonomer.

+135-3858-6433 (GuangDong) +188-1699-6168 (ShangHai) +852-6957-5415 (HongKong)

TPSeal® M3671 is intended for the manufacture of rotomoulded items and available in natural, in pellets or in powder.

It is also available under a black colour (TPSeal® M3670).

Main Characteristics

Its specific molecular structure ensures:

- Efficient binding with fuel barrier product such as Polyamide
- Excellent foaming properties

Application

Suitable for monolayer and multi-layer with foam technology.

Fuel tank production, with very low permeability. Structural parts. Water sports application.

Properties

Property	Method	Unit	Typical value (*)
Density (**)	ISO 1183	g/cm³	0.941
Melt Flow Rate (190°C-2.16kg)	ISO 1133/D	g/10min	3.5
Melting Temperature	ISO 11357	°C	126
Tensile modulus	ISO 527	MPa	650
Tensile strength @yield	ISO 527	MPa	18

(*) Data not intended for specification purposes

(**) Based on natural resin

Processing conditions

It is recommended to keep product dry prior use for production.