

Refining & Chemicals
Polymers

Technical Data Sheet
Metallocene Polyethylene Specialty Compound
Rotational Moulding
Produced in Europe

Description

Lumicene mPE M3421 UV is a new generation metallocene Medium Density Polyethylene (mMDPE) with hexene as comonomer.

Lumicene mPE M3421 UV is intended for the manufacture of rotomoulded items.

Lumicene mPE M3421 UV is a natural Specialty Compound available in pellets form.

Main Characteristics

Its specific molecular structure ensures:

- Superior mechanical properties
- > Improved dimensional stability
- > Easy processing

Application

Suitable for monolayer and multi-layer with foam technology.

Properties

Property	Method	Unit	Typical value (*)
Density (**)	ISO 1183	g/cm³	0.935
Melt Flow Rate (190°C/2.16kg)	ISO 1133/D	g/10min	2.7
Melting Point	ISO 11357	°C	123
Tensile Strength @ yield	ISO 527-2	MPa	18
Elongation at break	ISO 527-2	%	> 800
Tensile modulus	ISO 527-1B	MPa	590

(*) Data not intended for specification purposes (**) Based on natural resin

Processing conditions

It is recommended to keep product dry prior use for production.