

Description

Lumicene® Supertough 18ST05 is a polyethylene blown film grade that is especially designed to have an excellent processability on extrusion and conversion lines and to give a very high toughness – stability balance allowing new innovative multilayer film concepts. Thanks to this innovative design, Lumicene® Supertough 18ST05 brings a huge down-gauging potential in the film market and provides a breakthrough in blown film bubble stability.

Characteristics

Property	Method	Unit	Typical value
Density	ISO 1183	g/cm ³	0.918
Melt Flow Rate (190°C/2.16 kg)	ISO 1133	g/10 min	0.65
Melting temperature	ISO 11357	°C	115
Vicat temperature	ISO 306	°C	105

Values indicated are typical for this product. Density and MFR are properties routinely measured during "the standard quality control procedure". The other figures are generated by tests not included in the "standard quality control procedure", and are given for information only. Data are not intended for specification purposes.

Processing

Lumicene® Supertough 18ST05 is typically extruded at a melt temperature around 190°C and can be blown easily at any of the following conditions:

- Possibility to blend Supertough with a wide variety of products
- Optimal result in pure or in blend with low amount of another product in the same layer
- Wide range of thicknesses achievable
- Versatile product for different extrusion technologies : Low & High neck configuration, cast & MDO
- Temperature: 180 to 230°C
- BUR: 1.5:1 to 5.0:1
- Die gap: 1.2 to 2.8 mm

Additives

Antioxidant: yes

PPA: yes



Blown film properties

These values have been measured on a 40 µm blown film in low neck configuration.

Property	Method	Unit	Typical value (*)
Tensile Strength at Yield MD/TD (**)	ISO 527-3	MPa	11/11
Tensile Strength at Break MD/TD (**)	ISO 527-3	MPa	35/35
Elongation at Break MD/TD (**)	ISO 527-3	%	500/530
Elmendorf MD/TD (**)	ISO 6383-2	N/mm	65/125
Dart test	ISO 7765-1	g	>1700
Haze	ISO 14782	%	8
Gloss 45°	ASTM D2457		60

(*) Figures stated hereabove are obtained using laboratory test specimens produced with the following extrusion conditions: 45 mm screw diameter, L/D = 30, die diameter = 120 mm, die gap = 1.4 mm, BUR = 2.5:1, temperature = 195°C.