

Refining & Chemicals
Polymers

## Technical data sheet Polypropylene – Metallocene Random Copolymer

Produced in Europe

Polypropylene Lumicene® MR30MC2

## **Description**

Lumicene  $^{\circledR}$  MR30MC2 is a metallocene random copolymer with a Melt Flow Index of  $30^{(*)}$  g/10 min for injection moulding. Lumicene  $^{\circledR}$  MR30MC2 differs from the other random copolymers by its moulding reproducibility, outstanding organoleptic properties combined with low extractables, excellent transparency and gloss.

Producers of rigid food packaging, caps and closures, medical device and packaging, houseware and kitchenware will take full advantage of the new Lumicene $^{^{\circledR}}$  random metallocene product range.

We hereby confirm that we do not use peroxide in the manufacturing of the above-mentioned Product.

## **Characteristics**

	Method	Unit	Typical Value
Rheological properties			
Melt Flow Index 230°C/2.16 kg	ISO 1133	g/10 min	30 (*)
Mechanical properties			
Tensile Strength at Yield	ISO 527-2	MPa	31
Elongation at Yield	ISO 527-2	%	10
Tensile modulus	ISO 527-2	MPa	1300
Flexural modulus	ISO 178	MPa	1250
Izod Impact Strength (notched) at 23°C	ISO 180	kJ/m²	5
Thermal properties			
Melting Point	ISO 3146	°C	140
Other physical properties			
Density	ISO 1183	g/cm <sup>3</sup>	0.902
Bulk Density	ISO 1183	g/cm <sup>3</sup>	0.525

(\*) MFI 30 in metallocene catalyst system processes like MFI 20-25 in standard Ziegler Natta catalyst system.