



Polypropylene Circular Compound rPPH35NAT

Technical data sheet Homopolymer Produced in Europe

Description

Circular Compound rPPH35NAT is a high MFR high stiffness polypropylene of light grey color, containing at least 50% of post-consumer recycled (PCR) originating from post-consumer household waste collected in Western European countries.

Circular Compound rPPH35NAT is especially suited for injection molding applications. It is available in 1000 kg big-bag on 110x110 pallet or in bulk.

Circular Compound rPPH35NAT is not intended for food contact, pharmaceutical or medical applications.

Characteristics

	Method	Unit	Typical Value
Rheological properties			
Melt Flow Index 230°C/2.16 kg	ISO 1133	g/10 min	35
Mechanical properties			
Flexural modulus	ISO 178	MPa	1400
Charpy Impact Strength (notched), 23°C	ISO 179	kJ/m²	4
Physical properties			
Recycled content	EN15343	%	>50
Colour	RAL		ca. 7040
Density	ISO 1183	g/cm ³	0.970
Ash content	ISO3451-1	%	< 12
Humidity @110°C		%	< 0,1

