



TOTAL 道达尔
COMMITTED TO BETTER ENERGY

Refining & Chemicals
Polymers Orient

+135-3858-6433 (GuangDong)
+188-1699-6168 (ShangHai)
+852-6957-5415 (HongKong)

POLYSTYRENE 4241

Technical Data Sheet
High Impact Polystyrene
Manufactured in China

Description

- TOTAL POLYSTYRENE 4241 is a ductile high impact polystyrene for both extrusion and injection molding applications.
- This grade is especially suitable for the production of articles requiring good rigidity, dimension stability and high stiffness.

Applications

- Thermoformed Sheet
- Household Appliance

Properties	Method	Unit	Value (*)
Rheological			
Melt Flow Index (200°C / 5kg)	ISO 1133	g/10min	3.5
Spiral Flow (220°C)	-	cm	44
Thermal			
Vicat Softening Point 10N (T° increase = 50°C/h)	ISO 306	°C	95
Coefficient of Linear Thermal Expansion	-	mm/°C	9.1
Mechanical			
Notched Izod Impact Strength	ISO 180	kJ/m ²	11.5
Tensile Strength at Yield	ISO 527	MPa	25
Elongation at Break	ISO 527	%	55
Flexural Modulus	ISO 178	MPa	2150
Rockwell Hardness	ISO 2039	-	R99
Electrical			
Dielectric Strength	-	kV/mm	150
Surface Resistivity	ISO IEC 93	Ohms	>10 ¹³
Others			
Density	ISO 1183	g/cm ³	1.04
Moulding Shrinkage	-	%	0.4-0.7
Water Absorption	ISO 62	%	0.07
UL 94 Class	UL 94	-	HB

(*) Data not intended for specification purposes.

*All tests have been carried out at 23°C unless otherwise stated.

*Mechanical properties have been measured on injection molded test specimens.

*Bulk density is approximately 0.6 g/cm³.

General Information

- Processing condition: Temperatures during extrusion/injection should be below 240°C.
- Recommended Pre-Dry condition: 70°C for 2 hours.

Polystyrene