

PP

Impact copolymer for Injection Molding

► BJ700

● Description

BJ700 is high impact copolymer for injection molding application. They show an easy processability and an excellent stiffness combined with good impact strength. They can use various applications due to the well balanced mechanical property and processability.

● Characteristics

- Good processability
- High stiffness & impact strength
- Excellent appearance (gas mark & void etc.)

● Applications

- E&E parts, battery case, containers, industrial parts, toys

● Physical Properties

Typical Properties	Method (ASTM)	Unit	BJ700
Melt flow index	D1238	g/10min	25
Density	D1505	g/cm ³	0.91
Tensile strength at yield	D638	kg/cm ²	290
Elongation at break	D638	%	>150
Flexural modulus	D790	kg/cm ²	13,500
Izod impact strength at 23℃	D256	kgcm/cm	8
0℃			5
-20℃			4
Rockwell hardness	D785	R-scale	85
Heat distortion temp.	D648	℃	105

● **Food Contact Application**

- ▶ Hanwha Total BJ700 meet the FDA requirements in the Code of Federal Regulations in 21 CFR 177.1520 for food contact.
- ▶ In case you might need additional technical or regulatory information, please contact Hanwha Total Polymer Technical Service Team.