

PP

Impact copolymer for injection molding

► BJ600

● Description

BJ600 is for injection molding application. Hanwha Total impact copolymer shows an easy processability and an excellent stiffness combined with good impact strength & appearance.

● Characteristics

- Excellent balance between stiffness and impact strength
- Good appearance (gas mark and void free, high gloss)
- Good processability and productivity

● Applications

- E&E parts, battery case, containers

● Physical Properties

Typical Properties	Method (ASTM)	Unit	BJ600
Melt flow index	D1238	g/10min	15
Density	D1505	g/cm ³	0.91
Tensile strength at yield	D638	kg/cm ²	280
Elongation at break	D638	%	500
Flexural modulus	D790	kg/cm ²	13,000
Izod impact strength 23 °C	D256	kgcm/cm	9
0 °C			6
-20 °C			5
Rockwell hardness	D785	R-scale	85
Heat distortion temp.	D648	°C	105

● **Food Contact Application**

- ▶ There may be some limitation to apply Hanwha Total BJ600 to the food packaging. Thus, the verification on the suitability is necessary
- ▶ In case you might need additional technical or regulatory information, please contact Hanwha Total Polymer Technical Service Team.