

PRODUCT INFORMATION

CYROLITE® Med 2

Product Profile:

CYROLITE® Med 2 is a PMMA-based copolymer for injection molding and extrusion of medical applications.

Typical properties of CYROLITE® acrylic-based copolymer compounds are:

- High Light Transmittance with little haze
- 5 times the impact resistance of unmodified acrylics
- · Resistant to body fluids and many chemicals
- Excellent bonding to PVC tubing
- · Can be thermal bonded, ultrasonic and laser welded
- Good heat resistance
- Resistance to EtO, gamma and E-beam sterilization

The special properties of CYROLITE® Med 2 are:

- Superior resistance to lipids, blood, and oncology drugs
- Excellent resistance to alcohols and disinfectant wipes
- · Excellent ductility

Examples:

Filter Housings, Luer Locks, Connectors, Blood Separator, IV, Lab and Pediatric Filters.

Processing:

CYROLITE® Med 2 can be processed in injection molding machines and extrusion lines with 3- zone general purpose screws.

Physical Form / Packaging:

Available in 1500 lb. gaylord boxes; other packaging available on request.

Regulatory and compliance requirements:

Meets requirements of the United States Pharmacopeia Class VI in colorless (000) only; ISO 10993-1 in colorless (000) only and FDA for food contact for all use conditions up to and including hot filled or pasteurized above 150 degrees F (e.g. Condition 21 CFR 176.170) for all food types except those containing more than 8% alcohol.

Application:

Used for injection molding and extrusion of medical device and diagnostics industries.



Properties:				
	Parameter	Unit	ASTM-Standard	CYROLITE® Med 2
Mechanical Properties				Typical Value
Tensile Strength		psi [MPa]	D 638	5320 [36.7]
Tensile Modulus		x10º psi [GPa]	D 638	0.25 [1.7]
Tensile Elongation @ Yield		%	D 638	3.9
Tensile Elongation @ Break		%	D 638	22.0
Flexural Strength		psi [MPa]	D 790	8590 [59.2]
Flexural Modulus		x10º psi [GPa]	D 790	0.24 [1.6]
Notched Izod	¼" bar @23°C	ft-lb/in [J/m]	D 256	2.2 [117]
Rockwell Hardness		M Scale	D 785	33
Thermal Properties				
Vicat Softening Point	50N, 50°C/h	°F [°C]	D 1525	201 [94]
Deflection Temperature, Annealed	1.8MPa, 0.250"	°F [°C]	D 648	163 [73]
Coeff. of Linear Therm. Expansion	32 - 312ºF	1/F	D 696	0.000048
Coeff. of Linear Therm. Expansion	0 - 100°C	1/C	D 696	0.000086
Rheological Properties				
Melt Flow Rate	230°C & 5.0 kg	g/10min	D 1238	2.1
Optical Properties	d = 3.2 mm			
Light Transmission		%	D 1003	85
Haze		%	D 1003	7.0
Yellowness Index			E 313	-1.0
Other Properties				
Specific Gravity			D 792	1.08
Water Absorption		% Max	D 570	0.38
Mold Shrinkage		in/in, mm/mm	D 955	0.005 - 0.007
Bulk Density		g/cc	D 1895	0.65

All listed technical data are typical values intended for your guidance. They are given without obligation and do not constitute a materials specification.

IRÖHM