



PRODUCT INFORMATION

PLEXIGLAS® 7M

Product Profile:

PLEXIGLAS® 7M is based on polymethyl methacrylate (PMMA).

Besides showing the familiar properties of PLEXIGLAS® 7H molding compounds, such as

- excellent light transmission and brilliance
- · excellent weatherability
- high mechanical strength, surface hardness and abrasion resistance.

PLEXIGLAS® 7M is special in that it

- better flowing behavior,
- AMECA listing.

Application:

PLEXIGLAS® 7M is particularly suitable for extruding profiles and panels for use in lighting engineering.

Examples:

lighting fixtures, displays and similar extruded items for technical purposes.

Processing:

PLEXIGLAS® 7M can be processed on extruders with 3-zone general purpose screws for thermoplastics.

Physical Form / Packaging:

PLEXIGLAS® molding compound is supplied as pellets of uniform size in two-ply, 25kg polyethylene bags; other packaging on request.

For more information:

For more information, e.g. Charts or lists of resistance are in the database CAMPUS ® (http://www.campusplastics.com) free of charge.



Properties:

	Parameter	Unit	Standard	PLEXIGLAS® 7M
Mechanical Properties				
Tensile Modulus	1 mm/min	MPa	ISO 527	3200
Stress @ Break	5 mm/min	MPa	ISO 527	69
Strain @ Break	5 mm/min	%	ISO 527	4
Charpy Impact Strength	23°C	kJ/m²	ISO 179/1eU	20
Thermal Properties				
Vicat Softening Temperature	B / 50	°C	ISO 306	104
Glass Transition Temperature		°C	ISO 11357	108
Coeff. of Linear Therm. Expansion	0 - 50°C	E-5 /°K	ISO 11359	8
Flammability UL 94	1.5 mm	Class	IEC 60695-11-10	HB
Rheological Properties				
Melt Volume Rate, MVR	230°C / 3.8kg	cm ³ /10min	ISO 1133	2.9
Optical Properties	d=3 mm			
Luminous transmittance	D65	%	ISO 13468-2	92
Refractive Index	589nm/23°C		ISO 489	1.49
Other Properties				
Density		g/cm³	ISO 1183	1.19
Recommended Processing Conditions				
Predrying Temperature		°C		max. 94
Predrying Time in Desiccant-Type Drier		h		2 - 3
Melt Temperature		°C		220 - 260
Die Temperature (Extrusion)		°C		220 - 260

All listed technical data are typical values intended for your guidance. They are given without obligation and do not constitute a materials specification.

Certified to ISO 9001:2015, ISO 14001:2015 and IATF 16949:2016.

