



**PRODUCT INFORMATION** 

# PLEXIGLAS® Resist zk6HC

### Product Profile:

PLEXIGLAS® Resist zk6HC is an amorphous, impactmodified thermoplastic molding compounds (PMMA-I).

Typical properties of impact-modified PLEXIGLAS® molding compounds are

- high weather resistance
- excellent transmission and clarity
- brilliant appearance
- the pleasant feel and sound of the moldings.

PLEXIGLAS® Resist zk6HC is characterized by the following special properties:

excellent break resistance and impact strength
best resistance to stress cracking of all impactmodified PLEXIGLAS® molding compounds.

#### Application:

Used for extruding and coextruding sheets and profiles

#### Examples:

extruded/coextruded sheets and profiles for automotive bodies and the sanitaryware sector (bathtubs and shower trays) or crystal-clear luminaire covers for industrial plants that come into contact with aggressive media.

#### Processing:

PLEXIGLAS® Resist zk6HC can be processed on machines with 3-zone general purpose screws for engineering thermoplastics.

Physical Form / Packaging:

PLEXIGLAS® Resist zk molding compounds are supplied as pellets of uniform size in 25kg polyethylene bags or in 500kg boxes with PE lining; other packaging on request.



## **Properties:**

	Parameter	Unit	Standard	PLEXIGLAS® Resist zk6HC
Mechanical Properties				
Tensile Modulus	1 mm/min	MPa	ISO 527	1700
Yield Stress	50 mm/min	MPa	ISO 527	47
Yield Strain	50 mm/min	%	ISO 527	5.5
Nominal Strain @ Break		%	ISO 527	48
Charpy Impact Strength	23°C	kJ/m²	ISO 179/1eU	80
Thermal Properties				
Vicat Softening Temperature	B / 50	°C	ISO 306	97
Coeff. of Linear Therm. Expansion	0 - 50°C	E-5 /°K	ISO 11359	11
Classes of construction product			DIN EN 13501-1	E
Flammability UL 94	1.5 mm	Class	IEC 60695-11-10	HB
Rheological Properties				
Melt Volume Rate, MVR	230°C / 3.8kg	cm³/10min	ISO 1133	0.4
Optical Properties	d=3 mm			
Luminous transmittance	D65	%	ISO 13468-2	91
Refractive Index	589nm/23°C		ISO 489	1.49
Other Properties				
Density		g/cm³	ISO 1183	1.16
Water Absorption in Water	saturation, 23°C	%	ISO 62	1.8
Humidity Absorption	23°C / 50%	%	ISO 62	0.5
Recommended Processing Conditions				
Predrying Temperature		°C		max. 85
Predrying Time in Desiccant-Type Drier		h		2 - 3
Melt Temperature		°C		220 - 260
Die Temperature (Extrusion)		°C		220 - 260

All listed technical data are typical values intended for your guidance. They are given without obligation and do not constitute a materials specification.

Certified to ISO 9001:2015, ISO 14001:2015 and IATF 16949:2016.

