



Sinpolene FRF3014

Teknor Apex Asia Pacific PTE. LTD. - Polypropylene

General Information

General

Material Status	• Commercial: Active
Availability	• Asia Pacific
Features	• Flame Retardant • Halogenated
Forms	• Pellets
Processing Method	• Injection Molding

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.962		ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	15	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.010 to 0.012	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	3920	psi	ASTM D638
Tensile Elongation (Break)	68	%	ASTM D638
Flexural Modulus	151000	psi	ASTM D790
Flexural Strength	4350	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	1.3	ft-lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	212	°F	ASTM D648
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	V-0		UL 94

Notes

¹ Typical properties: these are not to be construed as specifications.