



APEX® 04-A0225A-75

Teknor Apex Company - Flexible Polyvinyl Chloride

General Information

General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Latin America • Asia Pacific • North America
Uses	• Industrial Applications
Regulatory Statement	• Due to the frequent updates to regulations, specifically, California Proposition 65, EU REACH SVHCs, and RoHS, please contact Teknor Apex for the most up to date compliance statement, or refer to section 15 of the product SDS.
Forms	• Pellets
Processing Method	• Extrusion

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.17		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	2100	psi	ASTM D638
Tensile Elongation (Break)	430	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec, Hand Held)	75		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	194	°F	ASTM D794
Brittleness Temperature	-83.2	°F	ASTM D746
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	25	%	ASTM D2863

Additional Information

Data Sheet Applies to Color(s) Listed Below:

Clear Blue 1 (0118109)

Wat Clr (0116633)

12/24 cw

Notes

¹ Typical properties: these are not to be construed as specifications.