



APEX® 07-U0296A-65

Teknor Apex Company - Flexible Polyvinyl Chloride

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Uses	• Wire & Cable Applications		
RoHS Compliance	• RoHS Compliant		
Appearance	• Opaque		
Forms	• Pellets		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.30		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	1900	psi	ASTM D638
Tensile Elongation (Break)	390	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	65		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	221	°F	ASTM D794
Brittleness Temperature	-49.0	°F	ASTM D746
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity (122°F)	3.1E+11	ohms·cm	ASTM D257
Dielectric Constant			ASTM D150
1 kHz	6.27		
1 MHz	3.75		
Dissipation Factor			ASTM D150
1 kHz	0.077		
1 MHz	0.12		
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	27	%	ASTM D2863

Notes

¹ Typical properties: these are not to be construed as specifications.