



APEX® 14-N6489B-81

Teknor Apex Company - Semi-Rigid Polyvinyl Chloride

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Latin America	
	• Asia Pacific	• North America	
Regulatory Statement	• Due to the frequent updates to regulations, specifically, California Proposition 65, EU REACH SVHCs, and RoHS, please contact Teknor Apex for the most up to date compliance statement, or refer to section 15 of the product SDS.		
Forms	• Pellets		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.28		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	3000	psi	ASTM D638
Tensile Elongation (Break)	430	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	81		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	140	°F	ASTM D794

Additional Information

Data Sheet Applies to Color(s) Listed Below:

Black 1 (1106223)

10/19 Core

Notes

¹ Typical properties: these are not to be construed as specifications.