



# APEX® 3300-90NT

Teknor Apex Company - Flexible Polyvinyl Chloride

## General Information

### General

|                   |                                          |                                            |                 |
|-------------------|------------------------------------------|--------------------------------------------|-----------------|
| Material Status   | • Commercial: Active                     |                                            |                 |
| Availability      | • Africa & Middle East<br>• Asia Pacific | • Europe<br>• Latin America                | • North America |
| Additive          | • Plasticizer                            |                                            |                 |
| Features          | • DEHP Plasticizer                       | • Ethylene Oxide Sterilizable              |                 |
| Uses              | • Food Service Applications              | • Medical/Healthcare Applications • Tubing |                 |
| Appearance        | • Clear/Transparent                      |                                            |                 |
| Forms             | • Pellets                                |                                            |                 |
| Processing Method | • Extrusion                              |                                            |                 |

## ASTM & ISO Properties <sup>1</sup>

| Physical                             | Nominal Value | Unit | Test Method |
|--------------------------------------|---------------|------|-------------|
| Density / Specific Gravity           | 1.27          |      | ASTM D792   |
| Mechanical                           | Nominal Value | Unit | Test Method |
| Tensile Strength (100% Strain)       | 2100          | psi  | ASTM D638   |
| Tensile Strength (Break)             | 3350          | psi  | ASTM D638   |
| Tensile Elongation (Break)           | 380           | %    | ASTM D638   |
| Hardness                             | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore C, 10 sec) | 65            |      | ASTM D2240  |
| Thermal                              | Nominal Value | Unit | Test Method |
| Brittleness Temperature              | -5.80         | °F   | ASTM D746   |

## Processing Information

| Extrusion        | Nominal Value | Unit |
|------------------|---------------|------|
| Melt Temperature | 375           | °F   |

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.