



APEX® 33042RV-60NT CBL B8 NP

Teknor Apex Company - Flexible Polyvinyl Chloride

General Information

General	
Material Status	Commercial: Active
Availability	- Africa & Middle East - Asia Pacific - Latin America - North America
Features	- ADM Compliant - BPA Free - DOTP Blend Plasticizer - E-beam Sterilizable - Ethylene Oxide Sterilizable - Latex Free - Non-Phthalate - Citrate Plasticizer - Non-Phthalate Plasticizer - Radiation (Gamma) Resistant - Radiation Sterilizable
Regulatory Statement	Due to the frequent updates to regulations, specifically, California Proposition 65, EU REACH SVHCs, and RoHS, please contact Teknor Apex for the most up to date compliance statement, or refer to section 15 of the product SDS.
Forms	Pellets
Processing Method	Extrusion

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.18		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
50% Strain	315	psi	
100% Strain	525	psi	
300% Strain	1160	psi	
Tensile Strength (Break)	1510	psi	ASTM D638
Tensile Elongation (Break)	430	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 15 sec, Operating Stand	55		
Shore A, 15 sec, Hand Held	60		

Additional Information

EXAMPLE EXTRUSION APPLICATIONS

Blood Pressure Tubing
 Blood Transport & Delivery
 Bubble Tubing
 Cable Jacketing
 Catheters
 Dialysis Tubing
 Drainage Tubing
 Endotracheal Airway Tubing
 Enteral Feeding Systems
 Infusion Tubing
 Oxygen Tubing
 Peristaltic Pump Tubing
 Suction Tubing

Data Sheet Applies to Color(s) Listed Below:
 Clear Blue B8 NP (1136598)

10/19 Core

+135-3858-6433 (GuangDong)
+188-1699-6168 (ShangHai)
+852-6957-5415 (HongKong)

APEX® 33042RV-60NT CBL B8 NP
Teknor Apex Company - Flexible Polyvinyl Chloride

Processing Information		
Extrusion	Nominal Value	Unit
Melt Temperature	315 to 335	°F

Notes

¹ Typical properties: these are not to be construed as specifications.