



APEX® 33043RV-65NT1 CBL B8 NP

Teknor Apex Company - Flexible Polyvinyl Chloride

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• BPA Free • DOTP Blend Plasticizer • E-beam Sterilizable • Ethylene Oxide Sterilizable	• Latex Free • No Animal Derived Components • Non-Phthalate - TOTM Plasticizer • Non-Phthalate Plasticizer	• Radiation (Gamma) Resistant • Radiation Sterilizable
Agency Ratings	• EC 1907/2006 (REACH)	• OEHHA (California) Proposition 65	
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		
Processing Method	• Extrusion		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.17		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
50% Strain	425	psi	
100% Strain	705	psi	
300% Strain	1490	psi	
Tensile Strength (Break)	1840	psi	ASTM D638
Tensile Elongation (Break)	420	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 15 sec, Operating Stand	59		
Shore A, 15 sec, Hand Held	65		

Additional Information

EXAMPLE EXTRUSION APPLICATIONS

Blood Pressure Tubing
Blood Transport & Delivery
Bubble Tubing
Cable Jacketing
Catheters
Dialysis Tubing
Drainage Tubing
Endotracheal Airway Tubing
Enteral Feeding Systems
Infusion Tubing
Oxygen Tubing
Peristaltic Pump Tubing
Suction Tubing

Data Sheet Applies to Color(s) Listed Below:
Clear Blue B8 NP (1136671)

+135-3858-6433 (GuangDong)
+188-1699-6168 (ShangHai)
+852-6957-5415 (HongKong)

APEX® 33043RV-65NT1 CBL B8 NP
Teknor Apex Company - Flexible Polyvinyl Chloride

Processing Information		
Extrusion	Nominal Value	Unit
Melt Temperature	320 to 340	°F

Notes

¹ Typical properties: these are not to be construed as specifications.