



APEX® 536

Teknor Apex Company - Flexible Polyvinyl Chloride

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Uses	• Connectors • Grommets	• Plugs • Strain Reliefs	
Wire Types	• Molded Components		
Agency Ratings	• UL QMFZ2		
RoHS Compliance	• RoHS Compliant		
Appearance	• Opaque		
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.39		ASTM D792
Molding Shrinkage - Flow	0.010 to 0.012	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	2230	psi	ASTM D638
Tensile Elongation (Break)	380	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	80		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-23.8	°F	ASTM D746
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index (CTI) (0.118 in)	PLC 0		UL 746
High Amp Arc Ignition (HAI) (0.12 in)	PLC 1		UL 746
Hot-wire Ignition (HWI) (0.12 in)	PLC 1		UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.06 in	V-0		
0.12 in	V-0		
Oxygen Index	24	%	ASTM D2863

Additional Information

Temperature Rating: 60 °C

Processing Information

Injection	Nominal Value	Unit
Processing (Melt) Temp	355	°F

Notes

¹ Typical properties: these are not to be construed as specifications.