



APEX® 6500-90

Teknor Apex Company - Flexible Polyvinyl Chloride

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Uses	• Connectors • Grommets	• Plugs • Strain Reliefs	
Wire Types	• Molded Components		
Agency Ratings	• UL QMFZ2		
RoHS Compliance	• RoHS Compliant		
Appearance	• Clear/Transparent		
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.26		ASTM D792
Molding Shrinkage - Flow	0.010 to 0.012	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	2580	psi	ASTM D638
Tensile Elongation (Break)	240	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	90		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	140	°F	ASTM D794
Brittleness Temperature	5.00	°F	ASTM D746
RTI Elec (0.06 in)	122	°F	UL 746
RTI Imp (0.06 in)	122	°F	UL 746
RTI Str (0.06 in)	122	°F	UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.12 in)	V-1		UL 94
Oxygen Index	24	%	ASTM D2863
Additional Information			
Temperature Rating: 60 °C			

Processing Information

Injection	Nominal Value	Unit
Processing (Melt) Temp	375	°F

Notes

¹ Typical properties: these are not to be construed as specifications.