



APEX® 74-8208-F

Teknor Apex Company - Flexible Polyvinyl Chloride

General Information			
General			
Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Low Gloss		
Uses	• Automotive Exterior Parts		
Automotive Specifications	• FORD ESB-M4D284-C4	• FORD ESB-M4D284-C4 Color: Various Colors	• GM GMP.PVC.012
Forms	• Pellets		
Processing Method	• Extrusion		

ASTM & ISO Properties ¹			
Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.33		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	2400	psi	ASTM D638
Tensile Elongation (Break)	360	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	85		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-13.0	°F	ASTM D746

Notes

¹ Typical properties: these are not to be construed as specifications.