



APEX® 80328

Teknor Apex Company - Flexible Polyvinyl Chloride

General Information

General			
Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Latin America • North America	
Features	• Direct Burial • Electrically Insulating	• Low Temperature Resistant • Oil Resistant	• Plasticized • Sunlight Resistant (720 hours)
Uses	• Appliance Wire Insulation • Appliance Wire Jacketing • Building Wire Insulation • Cable Jacketing	• Electronic Cable Jacketing • Flexible Cord Jacketing • Flexible Jacketing • Insulation	• Jacketing • Low Voltage Insulation • Wet Rated Insulation
Wire Types	• AWM • SJT	• SJTW • STW	
Agency Ratings	• UL 493 • UL 62 • UL 758	• UL 854 • UL I Oil Rating • UL QMTT2	• UL Type TW
Regulatory Statement	• Due to the frequent updates to regulations, specifically, California Proposition 65, EU REACH SVHCs, and RoHS, please contact Teknor Apex for the most up to date compliance statement, or refer to section 15 of the product SDS.		
Appearance	• Colors Available	• Opaque	
Forms	• Pellets		
Processing Method	• Wire & Cable Extrusion		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.43		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	2350	psi	ASTM D638
Tensile Elongation (Break)	350	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec, Hand Held)	85		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	176	°F	ASTM D794
Brittleness Temperature	-20.2	°F	ASTM D746
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity (122°F)	7.0E+11	ohms·cm	ASTM D257
Dielectric Constant			ASTM D150
1 kHz	5.22		
1 MHz	3.62		
Dissipation Factor			ASTM D150
1 kHz	0.067		
1 MHz	0.14		
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	23	%	ASTM D2863

APEX® 80328

Teknor Apex Company - Flexible Polyvinyl Chloride

Additional Information

Oil Rating: 4 Days @ 100CUL83

Data Sheet Applies to Colors Listed Below:

Natural (1014007)

2/20-lc

Notes

¹ Typical properties: these are not to be construed as specifications.