



APEX® 86-K264A-NT

Teknor Apex Company - Flexible Polyvinyl Chloride

General Information

Product Description

Non-Toxic Compound
Shore Hardness Measured at 15 sec. Delay
ACR @370°F, PSI 22, Die 20/1 Extrusion Time: 57 Seconds

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Appearance	• Clear/Transparent		
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.21		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	2390	psi	ASTM D638
Tensile Elongation (Break)	400	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	77		ASTM D2240

Notes

¹ Typical properties: these are not to be construed as specifications.