



APEX® 96-A0914K-106

Teknor Apex Company - Flexible Polyvinyl Chloride

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Uses	• Wire & Cable Applications		
RoHS Compliance	• RoHS Compliant		
Appearance	• Opaque		
Forms	• Pellets		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.58		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	2860	psi	ASTM D638
Tensile Elongation (Break)	240	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore C, 10 sec)	81		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	221	°F	ASTM D794
Brittleness Temperature	3.20	°F	ASTM D746
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	40	%	ASTM D2863

Notes

¹ Typical properties: these are not to be construed as specifications.