



APEX® CX 2017

Teknor Apex Company - Flexible Polyvinyl Chloride

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Latin America • North America	
Features	• Low Temperature Resistant	• Plasticized	• UV Stabilized
Uses	• Cable Jacketing • Coaxial Cable Jacketing	• Coaxial Cable Jacketing • Electronic Cable Jacketing	• Flexible Jacketing • Jacketing
Wire Types	• AWM		
Agency Ratings	• UL 1655	• UL 444	• UL 758
Regulatory Statement	• Due to the frequent updates to regulations, specifically, California Proposition 65, EU REACH SVHCs, and RoHS, please contact Teknor Apex for the most up to date compliance statement, or refer to section 15 of the product SDS.		
Appearance	• Colors Available	• Opaque	
Forms	• Pellets		
Processing Method	• Wire & Cable Extrusion		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.39		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	2310	psi	ASTM D638
Tensile Elongation (Break)	380	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 15 sec, Operating Stand	80		
Shore A, 15 sec, Hand Held	84		
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	167	°F	ASTM D794
Brittleness Temperature	-32.8	°F	ASTM D746
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	22	%	ASTM D2863

Additional Information

Data Sheet Applies to Colors Listed Below:

Natural (1121851)

Black 1 (1123563)

3/20-lc

Notes

¹ Typical properties: these are not to be construed as specifications.