+135-3858-6433 (GuangDong) +188-1699-6168 (ShangHai) +852-6957-5415 (HongKong)



APEX® S94-A0907C-80NT

Teknor Apex Asia Pacific PTE. LTD. - Flexible Polyvinyl Chloride

General Information

Product Description

APEX S94-A0907C-80NT is a Polyvinyl Chloride NSF Extrusion Compound available in clear and opaque granular form. It complies with NSF/ANSI STANDARD 61.

General

General		
Material Status	Commercial: Active	
Availability	Asia Pacific	
Features	Drinking Water Contact Acceptable	
Uses	• Hose	
Forms	Granules	

ASTM & ISO Properties 1

7.60 m & 100 1 10pointo			
Physical	Nominal Value Unit	Test Method	
Density / Specific Gravity	1.21	ASTM D792	
Mechanical	Nominal Value Unit	Test Method	
Tensile Strength ² (Break)	2900 psi	ASTM D638	
Tensile Elongation (Break)	350 %	ASTM D638	
Hardness	Nominal Value Unit	Test Method	
Durometer Hardness (Shore A)	79	ASTM D2240	

Additional Information

Typical temperature profile for processing compound is from 145°C to 185°C. The optimum temperatures depend on the type of machine as well as screw design being used to process.

Feeding zone: 145°C

Compression zone: 155°C to 165°C Mixing zone: 160°C to 170°C Nozzle/ Die zone: 170°C to 185°C

Notes

¹ Typical properties: these are not to be construed as specifications.

² 20 in/min