



FIREGUARD® 910A-80-NL

Teknor Apex Company - Flexible Polyvinyl Chloride

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Latin America • North America	
Features	• Flame Retardant	• Low Smoke Emission	
Uses	• Insulation, Plenum Cable	• Plenum Cable Jacketing	
Agency Ratings	• UL 13	• UL 1424	• UL 444
Regulatory Statement	• Due to the frequent updates to regulations, specifically, California Proposition 65, EU REACH SVHCs, and RoHS, please contact Teknor Apex for the most up to date compliance statement, or refer to section 15 of the product SDS.		
Appearance	• Colors Available	• Opaque	
Forms	• Pellets		
Processing Method	• Wire & Cable Extrusion		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.64		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	2190	psi	ASTM D638
Tensile Elongation (Break)	230	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore C, 10 sec, Hand Held)	84		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	167	°F	ASTM D794
Brittleness Temperature	1.40	°F	ASTM D746
Electrical	Nominal Value	Unit	Test Method
Dielectric Constant			ASTM D150
100 MHz	3.84		
250 MHz	3.78		
500 MHz	3.74		
Dissipation Factor			ASTM D150
100 MHz	0.019		
250 MHz	0.019		
500 MHz	0.018		
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	56	%	ASTM D2863

FIREGUARD® 910A-80-NL

Teknor Apex Company - Flexible Polyvinyl Chloride

Additional Information

Dynamic Thermal Stability @ 190°C, 80 RPM, #5 Bowl (Mins. To Decomposition) : 41..... ASTM D2538

Kayeness ACR @ 350°F, 1000 sec-1 (Pa-sec) : 427..... ASTM D3835

Cone Calorimeter @ 75 kW/m2 ISO5660

- Peak Heat Release Rate (kW/m²) : 97.7
- Average Heat Release Rate (kW/m²) : 54.6
- Total Heat Released (MJ/m²) : 74.4
- Average Heat of Combustion (MJ/kg) : 11.6
- Average Specific Extinction Area (m²/kg) : 187
- Peak Smoke (1/m) : 0.9

Data Sheet Applied to Color Listed Below:

Natural (1081124)

5/22-lc

Processing Information

Extrusion	Nominal Value	Unit
Melt Temperature	385	°F

Notes

¹ Typical properties: these are not to be construed as specifications.