



FIREGUARD® 910L16-C6-NL1

Teknor Apex Company - Flexible Polyvinyl Chloride

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Flame Retardant	• Low Smoke Emission	
Uses	• Plenum Cable Jacketing		
Wire Types	• CL2P • CL3P	• CMP • FPLP	• MPP • OFNP
Agency Ratings	• NEC Article 725 • NEC Article 760 • NEC Article 770	• NEC Article 800 • UL 13 • UL 1424	• UL 1651 • UL 444 • UL QMTM2
RoHS Compliance	• RoHS Compliant		
Appearance	• Opaque		
Forms	• Pellets		
Processing Method	• Extrusion		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.63		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	2200	psi	ASTM D638
Tensile Elongation (Break)	200	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore C	88		
Shore C, 10 sec	81		
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	167	°F	ASTM D794
Brittleness Temperature	-4.00	°F	ASTM D746
Electrical	Nominal Value	Unit	Test Method
Dielectric Constant			ASTM D150
1 kHz	4.75		
1 MHz	3.74		
Dissipation Factor			ASTM D150
1 kHz	0.063		
1 MHz	0.037		
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	46	%	ASTM D2863

FIREGUARD® 910L16-C6-NL1

Teknor Apex Company - Flexible Polyvinyl Chloride

Additional Information

Av.Sp. Extinction Area: 262 m²/kg
Avg. Heat of Combustion: 12.54 MJ/kg
Avg. Heat Rel. Rate: 67 kw/m²
Dynamic Heat Stability, 205°C, 100 rpm, 72 gms: 44
Kayeness ACR, 370°F, 1000 sec-1: 424 PA-sec
Peak Heat Rel. Rate: 111 kw/m²
Peak Smoke: 1.1 l/m
TA Six Digit Description: 0115306
Total Heat Rel'd: 62 MJ/m²

Processing Information

Extrusion	Nominal Value	Unit
Melt Temperature	380	°F

Notes

¹ Typical properties: these are not to be construed as specifications.