



FIREGUARD® 910A-69-NL

Teknor Apex Company - Flexible Polyvinyl Chloride

General Information

General

Material Status	• Commercial: Active	
Availability	• Africa & Middle East • Asia Pacific	• Latin America • North America
Features	• Flame Retardant	• Low Smoke Emission
Uses	• Insulation, Plenum Cable	• Plenum Cable Jacketing
Agency Ratings	• UL 13 • UL 1424	• UL 444 • UL QMTM2
Regulatory Statement	• Due to the frequent updates to regulations, specifically, California Proposition 65, EU REACH SVHCs, and RoHS, please contact Teknor Apex for the most up to date compliance statement, or refer to section 15 of the product SDS.	
Appearance	• Colors Available	• Opaque
Forms	• Pellets	
Processing Method	• Wire & Cable Extrusion	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.66		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	2000	psi	ASTM D638
Tensile Elongation (Break)	320	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore C, 10 sec, Hand Held)	69		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	167	°F	ASTM D794
Brittleness Temperature	-13.0	°F	ASTM D746
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	59	%	ASTM D2863

Additional Information

Dynamic Thermal Stability @ 190°C, 80 RPM, #5 Bowl (Mins. To Decomposition) : 27..... ASTM D2538

Cone Calorimeter @ 75 kW/m2 ISO5660

- Peak Heat Release Rate (kW/m²) : 94.1
- Average Heat Release Rate (kW/m²) : 50.7
- Total Heat Released (MJ/m²) : 58.2
- Average Heat of Combustion (MJ/kg) : 10
- Average Specific Extinction Area (m²/kg) : 131
- Peak Smoke (1/m) : 0.80

Data Sheet Applies to Color Listed Below:

Natural (1077482)

10/19-lc

Processing Information

Extrusion	Nominal Value	Unit
Melt Temperature	385	°F