



FLEXALLOY® 22-U14797A-90

Teknor Apex Company - Polyvinyl Chloride Elastomer

General Information

General			
Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Latin America • North America	
Features	• Electrically Insulating • Flame Retardant • Low Temperature Resistant	• Oil Resistant • Plasticized • Sunlight Resistant (300 hours)	• Sunlight Resistant (720 hours)
Uses	• Appliance Wire Insulation • Building Wire Insulation • Electronic Insulation • Flame Retardant Insulation	• Flexible Cord Insulation • Industrial Cable Insulation • Insulation • Retractable Cord Insulation	• Solid Insulation • Wet Rated Insulation
Wire Types	• AWM • SE • SEO • SEOOW • SEOW • SJE	• SJEO • SJEOW • SJEW • STE • STEOW • STEW	• SVE • SVEO • THHW • THW • TW • VW-1
Agency Ratings	• UL 1277 • UL 1685 • UL 62 • UL 758 • UL 83	• UL CL2 • UL I Oil Rating • UL II Oil Rating • UL QMTT2 • UL Type THHW	• UL Type THW • UL Type TW • UL VW-1
Regulatory Statement	• Due to the frequent updates to regulations, specifically, California Proposition 65, EU REACH SVHCs, and RoHS, please contact Teknor Apex for the most up to date compliance statement, or refer to section 15 of the product SDS.		
Appearance	• Colors Available	• Opaque	
Forms	• Pellets		
Processing Method	• Wire & Cable Extrusion		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.28		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	2830	psi	ASTM D638
Tensile Elongation (Break)	340	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 15 sec, Hand Held	90		
Shore A, 15 sec, Operating Stand	83		
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	221	°F	ASTM D794
Brittleness Temperature	-50.8	°F	ASTM D746
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	30	%	ASTM D2863

FLEXALLOY® 22-U14797A-90

Teknor Apex Company - Polyvinyl Chloride Elastomer

Additional Information

Data Sheet Applies to Color Listed Below:
Natural (1156720)

1/22-lc

Notes

¹ Typical properties: these are not to be construed as specifications.