



FLEXALLOY® 35033RV-55NT1

Teknor Apex Company - Flexible Polyvinyl Chloride

General Information			
General			
Material Status	Commercial: Active		
Availability	- Africa & Middle East - Asia Pacific	- Latin America - North America	
Features	- ADM Compliant - BPA Free - E-beam Sterilizable	- Ethylene Oxide Sterilizable - Latex Free - Non-Phthalate - TOTM Plasticizer	- Non-Phthalate Plasticizer - Radiation (Gamma) Resistant - Radiation Sterilizable
Regulatory Statement	Due to the frequent updates to regulations, specifically, California Proposition 65, EU REACH SVHCs, and RoHS, please contact Teknor Apex for the most up to date compliance statement, or refer to section 15 of the product SDS.		
Forms	Pellets		
Processing Method	Extrusion	Injection Molding	

ASTM & ISO Properties ¹			
Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.13		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
50% Strain	275	psi	
100% Strain	500	psi	
300% Strain	1210	psi	
Tensile Strength (Break)	1600	psi	ASTM D638
Tensile Elongation (Break)	410	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 15 sec, Hand Held	55		
Shore A, 15 sec, Operating Stand	50		

FLEXALLOY® 35033RV-55NT1

Teknor Apex Company - Flexible Polyvinyl Chloride

Additional Information

EXAMPLE EXTRUSION APPLICATIONS

Blood Pressure Tubing
Blood Transport & Delivery
Bubble Tubing
Cable Jacketing
Catheters
Dialysis Tubing
Drainage Tubing
Endotracheal Airway Tubing
Enteral Feeding Systems
Infusion Tubing
Oxygen Tubing
Peristaltic Pump Tubing
Suction Tubing

EXAMPLE INJECTION MOLDING APPLICATIONS

Adaptors
Blood Pressure Bulbs
Canulae
Caps
Connectors
Drip/Sight Chambers
Ear Protection
Endotracheal Airway Cuffs
Luers
Mouthpieces
Oxygen Masks
Personal Safety Goggles
Resuscitation Bags
Suction Bulbs
Syringe Bulbs
Valves

Data Sheet Applies to Color(s) Listed Below:

Clear Blue B8 NP (1136625)

CLR NP (1136223)

10/19 Core

05/2021: sp

Processing Information

Extrusion	Nominal Value	Unit
Melt Temperature	345 to 360	°F

Notes

¹ Typical properties: these are not to be construed as specifications.