



FLEXALLOY® 9633-80

Teknor Apex Company - Polyvinyl Chloride Elastomer

General Information

General

Material Status	• Preliminary Data		
Availability	• Africa & Middle East • Asia Pacific	• Latin America • North America	
Features	• Flame Retardant • Low Temperature Resistant	• Oil Resistant • Plasticized	• Sunlight Resistant (720 hours)
Uses	• Cable Jacketing • Coaxial Cable Jacketing • Communication Cable Jacketing	• Electronic Cable Jacketing • Flame Retardant Jacketing • Flexible Jacketing	• Industrial Cable Jacketing • Jacketing
Agency Ratings	• UL 1277 • UL 13 • UL 2250	• UL 444 • UL 62 • UL 758	• UL CL2 • UL I Oil Rating • UL II Oil Rating
Regulatory Statement	• Due to the frequent updates to regulations, specifically, California Proposition 65, EU REACH SVHCs, and RoHS, please contact Teknor Apex for the most up to date compliance statement, or refer to section 15 of the product SDS.		
Appearance	• Colors Available	• Matte Finish	• Opaque
Forms	• Pellets		
Processing Method	• Wire & Cable Extrusion		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.34		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	2260	psi	ASTM D638
Tensile Elongation (Break)	380	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 15 sec, Operating Stand	74		
Shore A, 15 sec, Hand Held	80		
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	221	°F	ASTM D794
Brittleness Temperature	-76.0	°F	ASTM D746
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	34	%	ASTM D2863

Additional Information

Data Sheet Applies to Color Listed Below:
Natural (1003038)

3/23-lc

Notes

¹ Typical properties: these are not to be construed as specifications.