



FLEXALLOY® 9610-78

Teknor Apex Company - Polyvinyl Chloride Elastomer

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Latin America • North America	
Features	• Flame Retardant • Low Temperature Resistant	• Oil Resistant • Plasticized	• Sunlight Resistant (720 hours)
Uses	• Appliance Wire Jacketing • Cable Jacketing	• Electronic Cable Jacketing • Flame Retardant Jacketing	• Flexible Cord Jacketing • Flexible Jacketing
Wire Types	• AWM • SE • SEO	• SEOOW • SEOW • SJE	• SJEO • SJEOW • SJEW
Agency Ratings	• UL 62	• UL 758	• UL QMTT2
Regulatory Statement	• Due to the frequent updates to regulations, specifically, California Proposition 65, EU REACH SVHCs, and RoHS, please contact Teknor Apex for the most up to date compliance statement, or refer to section 15 of the product SDS.		
Appearance	• Finishes Available	• Opaque	
Forms	• Pellets		
Processing Method	• Wire & Cable Extrusion		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.39		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	2340	psi	ASTM D638
Tensile Elongation (Break)	350	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec, Hand Held)	78		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	221	°F	ASTM D794
Brittleness Temperature	-36.4	°F	ASTM D746
Electrical	Nominal Value	Unit	Test Method
Dielectric Constant			ASTM D150
1 kHz	6.01		
1 MHz	3.94		
Dissipation Factor			ASTM D150
1 kHz	0.080		
1 MHz	0.058		
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	26	%	ASTM D2863

Additional Information

- Oil Rating:
- 7 Days @ 60°C UL62

Datasheet Applies to Color Listed Below:
Natural (1059495)
8/23-lc