



FLEXALLOY® 9606-65LG

Teknor Apex Company - Polyvinyl Chloride Elastomer

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Latin America • North America	
Features	• Flame Retardant • Low Gloss	• Low Temperature Resistant • Plasticized	• Sunlight Resistant (720 hours)
Uses	• Appliance Wire Jacketing • Cable Jacketing	• Electronic Cable Jacketing • Flame Retardant Jacketing	• Flexible Cord Jacketing • Flexible Jacketing
Wire Types	• AWM • SE • SEO	• SEOOW • SEOW • SJE	• SJEO • SJEOW • SJEW
Agency Ratings	• UL 62	• UL 758	• UL QMTT2
Regulatory Statement	• Due to the frequent updates to regulations, specifically, California Proposition 65, EU REACH SVHCs, and RoHS, please contact Teknor Apex for the most up to date compliance statement, or refer to section 15 of the product SDS.		
Appearance	• Colors Available	• Matte Finish	• Opaque
Forms	• Pellets		
Processing Method	• Wire & Cable Extrusion		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.23		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	2100	psi	ASTM D638
Tensile Elongation (Break)	390	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	65		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	221	°F	ASTM D794
Brittleness Temperature	-61.6	°F	ASTM D746
Electrical	Nominal Value	Unit	Test Method
Dielectric Constant			ASTM D150
1 kHz	6.01		
1 MHz	3.87		
Dissipation Factor			ASTM D150
1 kHz	0.075		
1 MHz	0.11		
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	26	%	ASTM D2863

FLEXALLOY® 9606-65LG

Teknor Apex Company - Polyvinyl Chloride Elastomer

Additional Information

Oil Rating:

- 7 Days @ 60C UL62

Datasheet Applies to Colors Listed Below:

Natural (0115095)

Black (1131643)

1/21-lc

Notes

¹ Typical properties: these are not to be construed as specifications.