



Sinvicomp SBF3742

Teknor Apex Asia Pacific PTE. LTD. - Rigid Polyvinyl Chloride

General Information

General

Material Status	• Commercial: Active	
Availability	• Asia Pacific	
Features	• Food Contact Acceptable	
Uses	• Film	• Shrink Wrap
Forms	• Granules	
Processing Method	• Blown Film	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.30		ASTM D792
Congo Red (374°F)	30.0	min	BS 2782
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	6670	psi	ASTM D638
Tensile Elongation (Break)	130	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	1.5	ft-lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	75		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	172	°F	ASTM D1525 ²

Notes

¹ Typical properties: these are not to be construed as specifications.

² Loading 1 (10 N)