



Sinvicomp DFR2704

Teknor Apex Asia Pacific PTE. LTD. - Rigid Polyvinyl Chloride

General Information

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific		
Features	• Good Impact Resistance		
Uses	• Foam	• Profiles	
Forms	• Powder		
Processing Method	• Extrusion		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Bulk Factor	0.65		ASTM D1895
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	31900	psi	ISO 178
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	174	°F	ASTM D1525
Heat Stability (356°F)	1.0	hr	ASTM D2115

Notes

¹ Typical properties: these are not to be construed as specifications.